

BUMA-WP®

BUMALASTIC

High flexible, two components, polymer modified cementitious liquid applied water impermeable



High elongation

UV, weather resistance

Multi-applications

Easy to use



BUMATECH CO., LTD

Factory: 820 Chanh Hamlet, Duc Lap Ha, Duc Hoa, Long An Province

Telephone: 028.3868 3803

Email: info@bumatech.com.vn

Website: www.bumatech.com.vn

PRODUCT DESCRIPTION

BuMaLastic is a two-component seamless waterproofing membrane polymer modified which cures to form a tough flexible membrane to protect all concrete and masonry surfaces against the ingress of water and moisture. Zero VOC certification

USES

- Waterproofing of external wall of building
- Waterproofing of basement walls
- Waterproofing of potable water tanks
- Waterproofing of kitchens and toilets
- Waterproofing of balconies and planter boxes
- Waterproofing of swimming pools and water features
- Waterproofing to precast gable end wall
- Waterproofing to RC flat roof and gutters
- Protection of concrete surfaces which may come into contact with seawater or sodium/ calcium chloride, and sulfates

SUITABLE SUBSTRATES

- Cement plaster
- Cement mortar beds
- Existing tile and stone
- Cement backer board
- Concrete

PACKAGING:

- 7.5kg/set: 3kg liquid + 4.5kg powder packed in 10L pail
- 25kg/set: 10kg liquid/can + 15kg powder/bag
- 25kg/set: 10kg liquid/20L pail + 15kg powder/bag

COVERAGE

- 1.5 – 2.0 kg/m²: external wall, wet area
- 3.0 – 4.0kg/m²: basement walls, pools, roofs

SHELF LIFE

Factory sealed containers of this product are guaranteed to be of first quality for two (2) years* if stored off the ground in a dry area and low temperature

* High humidity and temperature will reduce the shelf life of bagged product

RECOMMENDATIONS

- DO NOT use over dynamic expansion joints, structural cracks or cracks with vertical differential movement
- DO NOT use for thick coat (more than 1kg/m²/layer)
- DO NOT use over cracks >1.5mm in width
- DO NOT expose to negative hydrostatic pressure, excessive vapor transmission
- DO NOT add water, cement or fine aggregate to mixture

- DO NOT use for lightweight concrete (AAC block, panel...)
- DO NOT apply product if moisture of substrate higher than 6%, relative humidity higher than >85%
- During hot weather, keep product out of direct sunlight (powder and liquid) 6%, relative humidity higher than >85%

INSTALLATION**Concrete substrate preparation**

- Concrete surface should be structurally sound, clean and free from all dirt, oil, grease, adhesives, paint, sealers or curing compounds
- Repair cracks present in the concrete substrate with **BUMA-SP Bond 81** by injection method
- Concrete surface must be mechanically roughened prior to application. All substrates must have minimum ICRI CSP 2 to 3 (Grinding, high pressure water-jet blasting, light sandblasting, scarification... Bonding strength of surface must be at least 1.5MPa according to ASTM C1583
- Dampened the substrate before application

Mortar bed/ plaster substrate preparation

- Cementitious surface must be fully cured (7 days per 10mm thickness)
- Cementitious surfaces should be structurally sound, clean and free from all dirt, oil, grease, adhesives, paint, curing compounds
- Bonding strength of surface must be at least 0.5MPa according to ASTM C1583
- Dampened the substrate before application

Existing Ceramic Tile, Stone or Cement Terrazzo substrate preparation

- All tile and stone must be well adhered to the substrate and free from any bond breaking or bond-inhibiting surface contaminates. Ensure bond strength of the tile or stone to the substrate is a minimum 0.5MPa. If the floor does not pass 0.5MPa pull out strength test, must remove the tile or stone
- Existing tile or stone should be abraded by mechanically method
- Wash and rinse thoroughly with clean water. Allow to completed dry

Mixing

- Mixing ratio: mix 1.5 kg powder mix with 1.0 kg liquid
- Well shake liquid (Part A) and pour to clean pail
- Add **BuMaLastic** powder (Part B) to liquid and mix with low-speed mixer (to avoid air bubbles in mixture) to a smooth, fluid consistency.
- Avoid powder stuck the sides or the bottom of mixing pail

Application

- For horizontal and vertical surfaces, a roller, brush or spray gun can be used to apply the slurry. Care must be

taken to ensure that air is not entrapped in the membrane

- Ensure that all joints and corners are properly coated, preferable with a brush at the beginning
- **BuMaTape/ BuMaBand** is also recommended at joints and corners where movement is expected
- Apply the first coat of **BuMaLastic** and allow it to dry. Allow membrane to dry for approximately 1-2 hours before application of the second coat
- Apply the second coat of **BuMaLastic** at right angles to the first coat, allow a minimum curing time at least 72 hours before laying tile or commencing ponding test
- For exposed applications, **BuMaMesh 150/75** should be incorporated. Apply the first coat of **BuMaLastic** and immediately incorporated **BuMaMesh 150/75**. Apply subsequent coats at right angles to the last coat while ensuring ample coverage at all joints and corners

Installing tiles on BuMaLastic

- Allow **BuMaLastic** to cure 72 hours at 29°C and 50%RH before covering with tiles
- Ceramic/ porcelain/ granite tile, natural stone must be installed by the thin bed method with a Bumatech C2 Thin-Set Mortar: **BuMaSet, BuMaBond, BuMaFlex, BuMaEco + Ceralastic, Porcerapid**

Installing skimcoat or acrylic coating

- Allow **BuMaLastic** to cure 7 days at 29°C and RH \geq 50% before covering with skimcoat or another acrylic resin-based paint such as: **BuMaSkim, Skim 2in1, Proof 668...**

Cleaning

- Due to high adhesion strength of this product (even on metals), tools should be washed before mixture becomes harden
- Once mixture setting, cleaning can only be carried out by mechanical method

SAFETY PRECAUTIONS

- In case of contact with the eyes, rinse with running water (10-15min)
- Wear protective gloves, clothing and eye and face protection.
- Avoid inhaling dust/fume/mist of product (when use spray application)
- Ensure adequate ventilation during mixing and application
- Material Safety Datasheet will be supplied upon request

DISCLAIMER

- Technical details and recommendations contained in this product datasheet correspond to the best of our knowledge and experiences at the time of printing

- These detail offered for user's consideration and evaluation. It is the responsibility of the user to conduct their own tests to validate the suitability of the products for their requests
- Technical details and recommendations can be changed by site condition and workmanship of applicators.
- As we have no control over site conditions and the execution of the work, we accept no liability for any loss or damage which may rise as a result thereof. We also reserve the right to update the information at any time without prior notice to you to reflect our ongoing research and development program
- The newest technical data sheet will be supplied upon user request

TECHNICAL SERVICES/ AVAILABILITY

Information is available by calling

BUMATECH CO., LTD

Office: 154/1/5 Cong Lo, Ward 15, Tan Binh District, Ho Chi Minh City

Factory: 820 Chanh Hamlet, Duc Lap Ha Ward, Duc Hoa District, Long An Province

Technical : 028. 3910 0814

Sale : 028. 3868 3803

Email : info@bumatech.com.vn

Website : www.bumatech.com.vn

PRODUCT PERFORMANCE PROPERTIES

Test	Test Method	Specification	≥ 2.0 kg/m ²
Initial tensile adhesion strength	BS EN 14891	≥ 0.5 N/mm ²	≥ 1.1 N/mm ²
Tensile adhesion strength after water contact		≥ 0.5 N/mm ²	≥ 1.0 N/mm ²
Tensile adhesion strength after heat ageing		≥ 0.5 N/mm ²	≥ 1.3 N/mm ²
Tensile adhesion strength after contact with lime water		≥ 0.5 N/mm ²	≥ 1.0 N/mm ²
Tensile adhesion strength after contact with chlorinated water		≥ 0.5 N/mm ²	≥ 1.0 N/mm ²
Water impermeability		No Penetration	Pass
Crack bridging ability		≥ 0.75 mm	≥ 1.25 mm
Crack bridging ability when combine with BuMaMesh 70/ 150			≥ 2.20 mm
28 Days Elongation at break	ASTM D412	n/a	200% ± 30%
Maximum tensile strength			≥ 1.0 MPa
Shore A hardness	ASTM D2240		≥ 55
Pot life (35°C, RH ≥ 60%)	n/a	n/a	~ 1 hour
Tack free time (35°C, RH ≥ 60%)			~ 2 hours
Fully cure (35°C, RH ≥ 60%)			~ 7 days

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions