

**BUMA-WP®** 

# **BUMAMESH 150**


Alkalis resistant fiberglass mesh use reinforced waterproofing, plaster

# Resistant to alkalis

Good tensile strength

Anti - fracture

# Easy to use









Factory: 820 Chanh Hamlet, Duc Lap Ha, Duc Hoa, Long An Province

Telephone: 028.3868 3803

Email: info@bumatech.com.vn

Website: www.bumatech.com.vn

#### PRODUCT DESCRIPTION

**BuMaMesh 150** is made from glass fibers with synthetic resin coating which makes it resistant to alkalis. It is used to reinforce waterproofing layers, anti – fracture membranes and cementitious smoothing layers. Once these layers where the mesh is installed has hardened, **BuMaMesh 150** reinforce the layers to protect against formation of cracks due to movement in the substrates

#### **USES**

- ■Reinforce for cementitious waterproofing liquid applied BuMaLastic, Flex WP 2K
- ■Reinforce for Acrylic waterproofing membrane Proof 668
- Reinforce for cementitious skimcoat **BuMaSkim I/E, Skim 2in1**, for crack, joint treatment for interior and exterior

PACKAGING: 1m x 50m/ roll, 4 rolls/ carton box

**COLOUR:** Blue with white logo

#### SHELF LIFE

The product may be stored for several years in a clean, dry and cool place

#### **LIMITATIONS**

- Install only at temperatures between 8°C and 35°C.
- •Keep product away from heat source

# PRODUCT PERFORMANCE PROPERTIES

Characteristic	Result
Weight (g/m2)	~150
Mesh size	5 x 5
Tensile strength	Long. ≥ 1300 N/5cm Trans. ≥ 1100 N/5cm
Tensile strength after	Long. ≥ 350 N/5cm
immerse in lime water 7 days	Trans. ≥ 450 N/5cm
Crack bridging ability, used with BuMaLastic (3.0kg/m2)	≥ 2.20mm

### INSTALLATION

Refer relevant product technical datasheets

# **SAFETY PRECAUTIONS**

It is recommended to wear gloves and goggles during use product

# **TECHNICAL SERVICES/ AVAILABILITY**

Information is available by calling

**BUMATECH CO., LTD** 

Office: 154/1/5 Cong Lo, Ward 15, Tan Binh

District, Ho Chi Minh City

Factory: 820 Chanh Hamlet, Duc Lap Ha Ward,

Duc Hoa District, Long An Province

Technical: 028. 3910 0814 Sale : 028. 3868 3803

Email : info@bumatech.com.vn Website : www.bumatech.com.vn